

Technical Data Sheet N° WPSIT0047-17.02

DESCRIPTION

Synthetic PVC-P membrane obtained by cast process, dimensionally stabilized by glass fiber and coupled on the back sheet with 300 gr/m² TNT polyester.

Manufactured in a plant certified UNI EN ISO 9001 (Quality management system) and UNI EN ISO (environmental management system).

Setting performed by applicators approved by Flag S.p.A. Finishing and accessories composed by elements produced and approved by Flag S.p.A.

FEATURES

- Weatherproof and UV resistance
- Dimensional stability
- Resistant to puncturing
- RAL colouring available on request for landscape or architectural purposes

AREA OF USE

ROOFING

- Total adherence on horizontal surfaces for:
 - refurbishment of existing roofing, in contact with bituminous surfaces
 - gluing on support with bituminous membrane

PROPERTIES

		SFb 1,50	SFb 1,80	SFb 2,00	SFb 2,40	Test method
Thickness	(mm)	1,50	1,80	2,00	2,40	EN 1849-2
Weight	(kg/m²)	2,10	2,45	2,70	3,20	EN 1849-2
Tensile strength	(N/5cm)	≥ 800	≥ 950	≥ 1000	≥ 1200	EN 12311-2
Elongation to break	(%)	≥ 80	≥ 80	≥ 80	≥ 80	EN 12311-2
Tear resistance	(N)	≥ 250	≥ 270	≥ 300	≥ 330	EN 12310-2
Resistance to impact on rigid support	(mm)	≥ 900	≥ 1000	≥ 1250	≥ 1500	EN 12691
Cold bending	(°C)	≤ - 25	≤ - 25	≤ - 25	≤ - 25	EN 495-5
Hydrostatic pressure resistance (6 hours at 0,5 Mpa)		waterproof	waterproof	waterproof	waterproof	EN 1928 met. B
Dimensional stability (6 hours at 80°C)	(%)	≤ 0,1	≤ 0,1	≤ 0,1	≤ 0,1	EN 1107-2
Resistance against artificial ageing	(UV)	No surface cracking	No surface cracking	No surface cracking	No surface cracking	EN 1297
Resistance to roots penetration		No penetration	No penetration	No penetration	No penetration	EN 13948
Resistance to static punching	(kg)	≥ 20	≥ 20	≥ 20	≥ 20	EN 12730
Fire resistance		E	E	E	Е	EN ISO 11925-2 EN 13501-1

PRODUCTION STANDARD

Thickness	mm 1,50	mm 1,80	mm 2,00	mm 2,40		
Width	m 1,60	m 1,60	m 1,60	m 1,60		
Number of rolls on each pallet	16	12	12	12		
Length	m 20	m 20	m 20	m 20		
Colour (surface / underside)	LIGHT GREY / TNT					

System data sheet: • 4b1; refurbishment of existing waterproofing

CE MARKING

Unique identification code of the product-type: WPSIT0047

FLAGON SFb membranes are produced by the FLAG Spa factory (SOPREMA group) in Villa Santo Stefano are CE marked no.1085-CPR-018 in accordance with EN 13956:2012.

Due to its formulation, the liner is NOT subject to the requirements set forth in the CLP Regulation (EC) No 1272/2008 and EU n° 487/2013 and subsequent amendments on dangerous substances. If the product should be disposed of as a waste, we recommend sending it to an authorised landfill site or to an incinerator equipped with post-combustion chamber and fumes washing system. The data herewith indicated, apart from those required by EC branding, are not exhaustive and Flag SpA may modify them without previous notice. Flag SpA, has the right to modify the product at any time and without previous notice, in any of its aspect, and to stop its production.

Flag SpA reserves the right, as technology and know-how progress, to modify without warning the composition and conditions of use of its materials, and subsequently their price. As a result, orders shall only be accepted on the basis of the terms and technical specifications applicable at the time of receipt.





www.soprema.it

e-mail: tech-office@flag.it